



Wiltshire Ballistic Services Ltd

The Ranges, Station Road, Devizes

Wiltshire, SN10 1BZ, UK

Tel: +44 (0)1380 721644 Fax: +44 (0)1380 721421

<http://www.wiltshireballistics.co.uk>

FG Glass Industries Pvt. Ltd.
1204 Tower A
Nman Midtown.
Lower Parel
Mumbai
400 013

Trial Number 10933d

26 May 2021

BALLISTIC TEST REPORT

Please find attached, reports for the following test/s carried out at Wiltshire Ballistic Services on 14 May 2021.

Sample Name	Description	Results
BRG-BR2	BSEN 1063:2000 BR2 9x19mm DAG DM11 A1B2 124gr	Passed BSEN 1063:2000 BR2 NS

The results contained in this report are only valid for the samples tested and detailed above. The publication of these results in any abridged form is not allowed without approval by Wiltshire Ballistic Services Ltd. in writing.

For and on behalf of Wiltshire Ballistic Services Ltd

26 May 2021



Wiltshire Ballistic Services Ltd
The Ranges, Station Road,
Devizes, Wiltshire, SN10 1BZ
Tel: 01380 721644
Fax: 01380 721421

TEST REPORT
10933d - WBS - 14/05/2021
26 May 2021

FG Glass Industries Pvt. Ltd.
1204 Tower A
Nman Midtown.
Lower Parel
Mumbai
400 013

Trial Number 10933d
Trial Date 14/05/2021
Trial Start Time
Trial Finish Time

Range Temp (°C) 0
Range Humidity (%) 0
Range Pressure (mBar)
Range Technician Joseph Jones
Range Technician Andrew Collins-Frampton
Range Technician

Report Completed

James Philbrook

Approved Signatory

Sharon Pfeleger-Taylor

BALLISTIC TEST DETAILS

BSEN 1063:2000 BR2

Velocity From (m/s) 390 **Witness Type** Aluminium Foil **Configuration - Muzzle to Target (m)** 5.0
Velocity To (m/s) 410 **Ammunition** 9x19mm DAG DM11 A1B2 124gr **Configuration - Muzzle to Chrono Centre (m)** 2.5

SAMPLE DETAILS

BRG-BR2

FG Glass Industries Pvt Ltd

FG1 - Measured thickness: 20.61mm

Size (mm): 500x500 Weight (kg): 10.7

Shot No.	Velocity m/s	Held/ Penetrated	Trauma Code/ Spall Rating	Comments
1	407.29	Held	No Spall	
2	400.89	Held	No Spall	
3	405.10	Held	No Spall	

SAMPLE DETAILS

BRG-BR2

FG Glass Industries Pvt Ltd

FG2 - Measured thickness: 21.47mm

Size (mm): 500x500 Weight (kg): 10.85

Shot No.	Velocity m/s	Held/ Penetrated	Trauma Code/ Spall Rating	Comments
1	397.95	Held	No Spall	
2	409.53	Held	No Spall	
3	416.77	Held	No Spall	

SAMPLE DETAILS

BRG-BR2

FG Glass Industries Pvt Ltd

FG3 - Measured thickness: 21.59mm

Size (mm): 500x500 Weight (kg): 10.85

Shot No.	Velocity m/s	Held/ Penetrated	Trauma Code/ Spall Rating	Comments
1	398.82	Held	No Spall	
2	397.49	Held	No Spall	
3	404.30	Held	No Spall	

BRG-BR2

RESULTS
BSEN 1063:2000 BR2

Passed BSEN 1063:2000 BR2
NS

END OF REPORT